

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE

TEST REPORT
DENEY RAPORU



AB-0583-T
21020672
07-21

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. AŞ.
Address: VELİMEŞE OSB. MAH. HACI ŞEREMET SOKAK 9/9 ERGENE/TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: ArShirt-3938,Navy
Name and identity of test item: Navy blue knitted fabric.
The date of receipt of test item: 28.06.2021
Re-submitted/re-confirmation date: -
Date of test: 28.06.2021-02.07.2021
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not Specified
Number of pages of the report: 3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
02.07.2021

Customer Representative
Servin YILIRSEVEN

Head of Testing Laboratory
Sevim A. BAZAK
02.07.2021

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.


AB-0583-T

21020672

07-21

REQUIRED TESTS	RESULT	COMMENTS
COLOR FASTNESS TESTS		
Color Fastness to Hot Pressing	-	
No requirement was given by vendor		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. Tests marked (*) in this report are not included in the accreditation schedule.



Gen.f136-2/03

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid

EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.

AB-0583-T

21020672

07-21

TEST RESULTS

HOT PRESSING; ISO 105 X11:1994

Atlas Scorch Tester. 110 ±2 °C. 15 seconds

ISO 105 F02-Cotton adjacent fabrics were used.

Performed in the conditioned room (20±2°C-65%±4)

Evaluated with ISO 105 A02 and ISO 105 A03 standart grey scale.

	<u>Colour change</u>	<u>Staining</u>	<u>REQUIREMENT</u>
Before conditioning			
Dry	4-5	-	-
Steamy Press	4-5	4-5	-
Wet	2-3	4-5	-
After conditioning			
Dry	4-5	-	-
Steamy Press	4-5	4-5	-
Wet	4-5	4-5	-

Gen. fl136-2/03