



**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**  
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar  
İstanbul/ TÜRKİYE

**TEST REPORT**  
DENEY RAPORU




AB-0583-T
23004402
02-23

**Customer name:** ARITEKS BOYACILIK TİCARET VE SAN.AŞ.  
**Address:** VELİMEŞE OSB MAH. HACIŞEREMET 5.SOKAK 9/9 ERGENE/TEKİRDAĞ  
**Contact Person:** ÖZGÜR KUŞKU  
**Order No:** -  
**Article No:** ArWowear T5 Soft El 3160  
**Name and identity of test item:** One sample of navy woven fabric  
**The date of receipt of test item:** 20.02.2023  
**Re-submitted/re-confirmation date:** -  
**Date of test:** 20.02.2023-24.02.2023  
**Remarks:** -  
**Sampling:** The results given in this report belong to the received sample by vendor.  
**End-Use:** -  
**Care Label:** -  
**Number of pages of the report:** 5

*The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.*

*EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.*

*The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.*



Seal

Date  
24.02.2023

Customer Representative  
Servin YURUSEVEN

Head of Testing Laboratory  
Sevim A. RAZAK  
24.02.2023

This report shall not be reproduced other than in full except with the permission of the laboratory.  
Testing reports without signature and seal are not valid.

EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.


AB-0583-T

23004402

02-23

REQUIRED TESTS	EVALUATION	COMMENTS
<b>PHYSICAL PROPERTIES TESTS</b>		
Pilling	-	-
No requirement was given by vendor.		

**REMARK:** Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor  $k=2$ , providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. Tests marked (\*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.  
*Testing reports without signature and seal are not valid.*

Gen.fl36-2/04

EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.

AB-0583-T

23004402

02-23

## TEST RESULTS

### PILLING ; ISO 12945-1:2020

ICI Pilling Box @60±2 rpm. The average results are given for 4 samples. Number of observer : 2  
Performed in the conditioned room (20±2°C-65%±4).  
The test samples were evaluated according to the visual grading tables in the ISO 12945-4 standard.  
Original sample was tested as the client's request .

5000 Revs	RESULT			REQUIREMENT
	Pilling	Fuzzing	Matting	
	4-5	4	NA	-

NA :Not applicable

	PILLING /FUZZING/MATTING GRADING
5	No change
4	Slight surface fuzzing and/or pilling/matting
3	Moderate surface fuzzing and/or pilling/matting
2	Distinct surface fuzzing and/or pilling /matting
1	Dense surface fuzzing and/or severe pilling/matting

Total uncertainty:±0.5 derece

Gen.f136-2/04