



EKOTEKS

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE

TEST REPORT
DENEY RAPORU

20020283

07-20

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Hacı Şeremet 4. Sok. 59850 YULAFLI/ ÇORLU/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: ArAir Mesh BB-4519 beyaz
Name and identity of test item: White knit fabric.
The date of receipt of test item: 18.06.2020
Re-submitted/re-confirmation date: 25.06.2020
Date of test: 25.06.2020-08.07.2020
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not Specified
Number of pages of the report: 3

Seal

Date
08.07.2020

Customer Representative
Özlem ULUS

Head of Testing Laboratory
Sevim A. RAZAK

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

20020283

07-20

REQUIRED TESTS	RESULT	COMMENTS
PHYSICAL PROPERTIES		
Breathability(Differential Pressure)	P	
P: Pass F: Fail R: Refer to retailer technologist. Test results were evaluated according to TSE K 599: 2020 limit values		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



Gen.f136-2/03

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

20020283

07-20

TEST RESULTS

BREATHABILITY (Differential Pressure)

Test Metodu: EN 14683:2019+AC :2019 (TS EN 14683+AC:2019) EK-C (*)

Test Condition (21 ± 5) °C ve (85 ± 5) % relative humidity, 4 hrs

Test area is 25 mm in diameter , 5 different sample was taken

Adjusted airflow is 8 l/min.The differential pressure is read directly using a differential pressure manometer .

ORIGINAL

SAMPLE	DIFFERENTIAL PRESSURE RESULT	REQUIREMENT
1	21,8 Pa/cm ²	< 60 Pa/cm ²
2	29,3 Pa/cm ²	
3	27,4 Pa/cm ²	
4	23,0 Pa/cm ²	
5	24,9 Pa/cm ²	
Average Result	25,3 Pa/cm ²	

Gen.f136-2/03