



EKOTEKS

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



Test
TS EN ISO/IEC 17025
AB-0583-T

**TEST REPORT
DENEY RAPORU**

AB-0583-T
20013631
05-20

Customer name: ARITEKS BOYACILIK TİCARET VE SAN. A.Ş.
Address: Hacı Şeremet 4. Sok. 59850 YULAFLI/ ÇORLU/ TEKİRDAĞ
Buyer name: -
Contact Person: ÖZGÜR KUŞKU
Order No: -
Article No: ArPowerKnitP-5938
Name and identity of test item: One sample of black knitted fabric. (Black)
The date of receipt of test item: 27.04.2020
Re-submitted/re-confirmation date: -
Date of test: 27.04.2020-05.05.2020
Remarks: -
Sampling: The results given in this report belong to the received sample by vendor.
End-Use: -
Care Label: Not specified.

Number of pages of the report: 3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports.

EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report.

Seal

Date
05.05.2020

Customer Representative
Özlem ULUS

Head of Testing Laboratory
Sevim A. RAZAK
05.05.2020

This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
20013631
05-20

REQUIRED TESTS	RESULT	COMMENTS
PHYSICAL PROPERTIES TESTS		
Spray Test	-	
No requirement was given by vendor.		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T
20013631
05-20

TEST RESULTS

SPRAY TEST; TS 259 EN 24920:2001

Performed in the conditioned room (21±1°C-65±4% RH)

Test was performed original sample.

Temperature of water 20°C.

	<u>RESULT</u>	<u>REQUIREMENT</u>
1.	ISO 5	-
2.	ISO 5	-
3.	ISO 5	-

	<u>SPRAY RATING SCALE</u>
100 ISO 5	No sticking or wetting of the specimen face
90 ISO 4	Slight random sticking or wetting of the specimen face
80 ISO 3	Wetting of specimen face at spray points
70 ISO 2	Partial wetting of the specimen face beyond the spray points
50 ISO 1	Complete wetting of the entire specimen face beyond the spray points
0	Complete wetting of the entire face of the specimen