

ArMoto



Heavy Warp Knit Fabrics for Shoes and Wind Jackets




Ariteks, founded as a family owned business in 1975, is the leading textile manufacturer company both in fashion and technical textiles.

By continuously developing high-end technologies it provides solutions to end users in apparel, protective workwear, functional sport, medical wear as well as technical textiles in construction and transportation industries.

As the pioneer company in special dyeing methods like indigo, vat, space-dye, coating and laminating systems, Ariteks produces highest-quality fabrics both for international and domestic markets.

Ariteks uses clean and renewable energy resources. It consumes minimum amount of water by using continuous optimised systems.

Based in 14000m² with 12 separate in house R&D laboratories, the company spends 5% of its budget for research and developing future technologies. It focuses especially on 3rd generation solar cells on flexible fabrics and biosensing textiles.



CONTENT

1	ArMoto 240 gr/m ² , 100% Polyester, Wind Jacket Fabric	4-5
2	ArMoto Dura 240 gr/m ² , 100% Pa 6.6, Warp Knit Fabric	6-7



240 gr/m², 100% Polyester,
Wind Jacket Fabric



Sample



ArMoto - 4349
Navy



ArMoto - 4350
Black



Description

100% Polyester wind jacket fabric. ArMoto can be used on motorcyclist cloths as air channel. For the shoes industry it is popular fabric to laminate on base and edge of sport shoes.

Technical Parameters

Name	Values	Standards
Fiber	100% Polyester (PES)	TS EN ISO 1833
Yarn	300 Denier	EN ISO 2060
Weight	240 ±5 gr/m ²	TS EN 12127
Width	1500 ±20 mm	TS EN 1773
Bursting strength	> 2500 kPa (kN/m ²)	TS EN 13938-1
Dimensional Change	-5%<Length<+5%;-5%<Width<+5%	TS EN ISO 5077
Abrasion Resistance	@50000	TS EN 530
Rubbing Fastness	4	EN ISO 105 X12
Perspiration Fastness	4-5	EN ISO 105 E04
Washing Fastness	4-5	EN ISO 105 C01
Dry Cleaning Fastness	4-5	EN ISO 105 D01
Hypochlorite Fastness	4-5	EN ISO 105 N01
Hot Press Fastness	4-5	EN ISO 105 X11
Light Fastness	4-5	EN ISO 105 B02
pH	6.2	EN ISO 3071
Azo Test	No Azo Colorants.	EN ISO 14362-1
Application	Wind Jacket, Shoes	
Quality Management	Done	ISO 9001



240 gr/m², 100% Pa 6.6,
Warp Knit Fabric



Sample



**ArMoto Dura - 5346
Black****ArMoto Dura - 5347
White**

The technical data on this guide is given for information and correct at the time of design. It can be changed without prior notice.

Description

100% Polyamide 6.6 warp knit fabric for heavy duty and military shoes.

ArMoto Dura is made of high tenacity polyamide fibers. For the military shoes industry it is popular fabric to laminate on base and edge of shoes.

Technical Parameters

Name	Values	Standards
Fiber	100% HT Polyamide (PA 6.6)	TS EN ISO 1833
Yarn	300 Denier	EN ISO 2060
Weight	240 ±5 gr/m ²	TS EN 12127
Width	1500 ±20 mm	TS EN 1773
Bursting strength	> 5000 kPa (kN/m ²)	TS EN 13938-1
Dimensional Change	-5%<Length<+5%;-5%<Width<+5%	TS EN ISO 5077
Abrasion Resistance	@50000	TS EN 530
Rubbing Fastness	4	EN ISO 105 X12
Perspiration Fastness	4-5	EN ISO 105 E04
Washing Fastness	4-5	EN ISO 105 C01
Dry Cleaning Fastness	4-5	EN ISO 105 D01
Hypochlorite Fastness	4-5	EN ISO 105 N01
Hot Press Fastness	4-5	EN ISO 105 X11
Light Fastness	4-5	EN ISO 105 B02
pH	6.2	EN ISO 3071
Azo Test	No Azo Colorants.	EN ISO 14362-1
Application	Military Shoes	
Quality Management	Done	ISO 9001

Fashion Fabrics



Technical Fabrics

  BUILDING	  HOME	  PROTECTION	  MEDICAL	  SPORT	  TRANSPORT
  GEOLOGY	  PACKAGE	  CLOTH	  AGRICULTURE	  ENVIRONMENT	  MACHINE

Headquarters

Hekimsuyu Cad. No:36
Kucukkoy/Gaziosmanpasa 34250 Istanbul/Turkey
Phone: +90 212 538 05 98-99
E-Mail: support@ariteksinfo.com
Web: www.ariteks.net

Factory

Velimese OSB Mah. 210. Sokak No:9/8
Ergene 59930 Tekirdag / Turkey
Phone: +90 282 676 41 90
E-Mail: support@ariteksinfo.com
Web: www.ariteks.net